

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
7 September 2001 (07.09.2001)

PCT

(10) International Publication Number  
**WO 01/64580 A1**

(51) International Patent Classification<sup>7</sup>: **C01B 33/18**,  
33/193, C09C 1/30, C08K 3/36, 3/38

(21) International Application Number: **PCT/EP01/02319**

(22) International Filing Date: 27 February 2001 (27.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
00200781.3 3 March 2000 (03.03.2000) EP

(71) Applicant (for all designated States except US): **AKZO NOBEL N.V. [NL/NL]**, Velperweg 76, NL-6824 BM Arnhem (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KUNKELER, Paulus, Johannes [NL/NL]**, Elkcuylgaard 120, NL-6227 EC Maastricht (NL); **DOKTER, Willem, Hendrik [NL/NL]**; Schepersstraat 7, NL-6191 VL Beek (NL).

(74) Agent: **SCHALKWIJK, Pieter, Cornelis**; Akzo Nobel N.V., Intellectual Property Dept. (Dept. AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

precipitated SiO<sub>2</sub>  
doped w/ Boron  
BET Surface area (p.a)  
low 187 m<sup>2</sup>/g  
Table 1

(54) Title: **AMORPHOUS SILICA PARTICLES COMPRISING BORON**

(57) Abstract: The invention pertains to an amorphous silica particle comprising 0.1 to 10<sup>5</sup> ppm boron atoms, and optionally 0.05 to 15 wt.% aluminum atoms wherein the boron and aluminum atoms are covalently bonded to the oxygen atoms of the silica network. The amorphous silica particles are used as a reinforcing filler for rubber articles, particularly for tires, more particularly for tire treads.

WO 01/64580 A1

## AMORPHOUS SILICA PARTICLES COMPRISING BORON

- 5 The present invention pertains to amorphous silica particles comprising boron atoms, to a method of preparation of the same, and to their use as reinforcement fillers.

10 Precipitated silica is increasingly used as a filler for elastomers, such as rubber, particularly for use in tires for motor vehicles. There is a continuing need for alternatives and improved products in this rapidly developing field. More particularly, industry is interested in precipitated silica that is even easier to disperse in said elastomer and/or shows a more time/cost-efficient treatment, e.g. with coupling agents, before being fully dispersible in the elastomer, and that will  
15 result in elastomer compositions (after vulcanization/curing) with low heat build-up, high wet grip, and low rolling resistance.

The presently claimed silica comprises boron atoms. In US 2,630,410 aqueous silica sols are disclosed the stability of which is improved by the addition of boric  
20 acid, sodium tetraborate, or the like. The boron compounds are only added to the silica sols as stabilizer, whereas the silica sol as such is not changed by the addition of said boron compound.

In DE 2,716,225 precipitated silica is disclosed containing 4-20 wt.% of  $B_2O_3$ . These silica compositions are used in organopolysiloxane elastomers. The  
25 silica of these compositions is not changed as such, but is obtained as particles impregnated with  $B_2O_3$ .

Recently, patent applications EP 943,648 and EP 941,995 were published, both of which pertain to rubber blends to which silica and a borate compound are added separately to improve the reaction rate between the silica and the added  
30 silane coupling agents.

It was now found that the use of a new specific type of precipitated silica results in a further improvement of the reaction rate between the silica and the silane coupling agent, and in an improvement of the dispersion of the silica particles in rubber compositions. The benefits of the instant invention reside in an amorphous silica particle comprising 0.1 to  $10^5$  ppm boron atoms, characterized in that the boron atoms are covalently bonded to the oxygen atoms of the silica network. More preferably, the silica particle comprises 10 to 125,000 ppm boron atoms.

Contrary to what is claimed in the standard literature (for example, Ralph K. Iler, *The Chemistry Of Silica*, John Wiley & Sons, 1979), built-in boron is not easily washed out or hydrolyzed from the silica framework and thus does not leach appreciably under the acidic conditions attained when the silica slurry from the precipitation is acidified to, for instance, pH 4.

In EP 631,982 silica aggregates were disclosed wherein in addition to or as replacement for Al, other elements such as Fe, Mg, B, P, and S can be introduced to tailor the silica towards its performance in an elastomer. However, it was not disclosed which improvement could be obtained with these elements, nor which of these element should be selected to obtain a desired improvement. These aggregates, moreover, have high SA BET values due to their method of production that uses aging temperatures between 15 and 50°C.

A further improvement was found when apart from the covalently bonded boron also covalently bonded aluminum is present in the silica network. Therefore, the amorphous silica may further comprise 0.05 to 15 wt.%, preferably 0.8 to 2 wt.%, aluminum atoms which are covalently bonded to the oxygen atoms of the silica network. This improvement was not found with the other elements that were disclosed in EP 631,982.

Surprisingly, a new process has been found to make these novel precipitated silica particles pre-eminently suitable for use as a replacement for conventional precipitated silica particles in elastomer compositions. More particularly, the

precipitated silica particles according to the invention can be characterized by a DBP oil absorption of 100-400 ml/100g, preferably 150-300 ml/100g, a BET surface area of 30-500 m<sup>2</sup>/g, preferably 50-300 m<sup>2</sup>/g, and more preferably 120-220 m<sup>2</sup>/g, and a CTAB surface area of 30-350 m<sup>2</sup>/g, preferably 50-300 m<sup>2</sup>/g, and more preferably 120-220 m<sup>2</sup>/g. The silica particles are preferably aged at a temperature of >60°C, more preferably at 65-90°C.

The methods for determining the DBP oil absorption, the BET and the CTAB surface area values are mentioned in the experimental part of the examples.

10 Preferably, the precipitated silica according to the invention has a pore volume of 0.55-0.85 ml/g when measured in accordance with DIN 66133 (applying a pressure from 7 to 500 bar) using an equilibrium time during the analysis of 30 seconds.

15 The precipitated silica according to the invention is suitably produced in one or more of the following manners:

- Boric acid (H<sub>3</sub>BO<sub>3</sub>) is dissolved in a water glass solution (SiO<sub>2</sub>/Na<sub>2</sub>O weight ratio about 3.3, containing 15-25, preferably 17.5-20, more preferably about 18.5 wt.% SiO<sub>2</sub>, and having a density of about 1.225 g/ml). Organic or inorganic acid (nitric acid, sulfuric acid, hydrochloric acid) is added, and the resulting boron-containing silica is filtered, washed, and dried.
- Boric acid is dissolved in a water glass solution. A water-soluble aluminum salt is added, and the resulting aluminum borosilicate is filtered, washed, and dried.
- 25 • Boric acid is dissolved in a water glass solution. An aluminum salt (e.g., sulfate, nitrate, phosphate) is added to an acid solution. The acid solution is added to the water glass solution, and the resulting aluminum borosilicate is filtered, washed, and dried.
- Borax (Na<sub>2</sub>B<sub>4</sub>O<sub>7</sub>·10H<sub>2</sub>O) is dissolved in water. Acid, optionally containing aluminum salts, may be added to increase the solubility. Borax solution,
- 30

water glass, and acid are simultaneously pumped into the reaction vessel. The resulting boron-containing silica is filtered, washed, and dried.

- Boric acid is dissolved in water, base may be added to increase solubility. Boric acid solution, water glass, and acid, optionally containing aluminum salts, are simultaneously pumped into reaction vessel. The resulting boron-containing silica is filtered, washed, and dried.
- Borax is dissolved in acid. Said acid is combined with water glass. The resulting boron-containing silica is filtered, washed, and dried.
- Borax and aluminum salts are dissolved in acid. This acidic solution is combined with water glass. The resulting aluminum borosilicate is filtered, washed, and dried.

Thus, generally, the amorphous silica particles of the invention can be made by a process comprising the steps of reacting an aqueous solution of water glass with boric acid and/or borax, and optionally also with an aluminum salt, at a pH of 10.5 or lower.

The silica particles are amorphous. Crystalline and glass-like particles are excluded, since these do not have advantageous properties when used as reinforcing filler in elastomers.

Since the effect of the instant silica particles is believed to reside at the surface of the particles, i.e. the number of free hydroxy groups at the surface of the particle, it is preferred that the boron atoms, and if present also the aluminum atoms, are contained at the surface of the particles. This can be achieved by first starting to make a conventional silica, and starting the addition of borax, boric acid, and aluminum salts after the initial stages of the silica manufacturing process.

Preferably, the sulfuric acid and the water glass are dosed below the level of liquid in the reactor, for example by using so-called dip-pipes, this in order to prevent high local concentrations of these components.

The weight ratio of the amount of  $\text{SiO}_2$  introduced via the dosed water glass in the first water glass dosage stage to the amount of aqueous medium in the reactor preferably is from 1:9.7 to 1:19.5, more preferably about 1:13.5.

- 5 Furthermore, the weight ratio of the amount of  $\text{SiO}_2$  introduced via the dosed water glass in the second water glass dosage stage to the amount of aqueous medium present in the reactor before the first dosage stage is from 1:24 to 1:46, preferably about 1:27.
- 10 It is to be understood that the term "precipitated silica" as used relates to precipitated silica in the powdered form. However, if so desired, the powder may be converted into granules, pearls, beads, or other similar shapes by means of compacting. For ease of handling, i.e. for (pneumatic) transport, reduced bridging in silos, and reduced dust formation, as well as for a more
- 15 efficient use of storage space, the precipitated silica is preferably compacted before use. Compaction may furthermore facilitate blending/mixing of the silica into the elastomer. Hence, a compacting step is preferably included in the process of the invention. The most preferred compacting step involves a granulation step. Optionally, the process involves a milling step to ensure that
- 20 the precipitated silica particles have a certain size distribution. It was found that the precipitated silica properties, *inter alia* the DBP oil absorption and the BET and CTAB surface areas, were hardly influenced by a granulation and/or a milling step.
- 25 The drying step in itself is not critical. As indicated, conventional drying steps, e.g. using a drying cabinet, spray-drying, flash drying, fluid bed drying, tray drying, rotary drying, and the like are all suitable. However, it was observed that the residence time of the precipitated silica in the dryer might influence its DBP oil absorption value. More specifically, drying times of just a few seconds to
- 30 minutes (at higher temperatures) typically resulted in precipitated silica with a DBP absorption value near the higher end of the specified range, while slow

drying, i.e. for tens of minutes or even hours, resulted in precipitated silica with a DBP absorption value near the lower end of the specified range.

The precipitated silica so obtained is pre-eminently suited for use in elastomers as a filler/reinforcing agent. The incorporation into the elastomer and the final elastomer composition are of the conventional type, except that the precipitated silica of the invention is applied. Favorable processing of the elastomer blend and excellent properties of the final elastomer article have been reported.

- 10 It is noted that the term "elastomer" as used throughout this document is meant to denominate all elastomeric compositions typically used in the industry. More particularly, it is a synthetic or natural rubber-comprising composition that may contain all the usual additives known in the art that are required to obtain finished articles comprising said (cured) compositions. As the use of the
- 15 precipitated silica in tires is of particular interest and because the precipitated silica according to the invention is pre-eminently suited to such use, the term "elastomer compositions" includes rubber compositions for use in tire treads. However, the precipitated silica according to the invention may also be used as a filler in rubber compositions for use as, e.g., motor mounts, conveyor belts,
- 20 and the like.

The following examples serve to illustrate the invention.

#### General

Chemicals used	Supplier
CaSO <sub>4</sub> ·2H <sub>2</sub> O	Merck, "foodgrade 516A"
Sulfuric acid	Baker, "analyzed, 95-97%", or Akzo Nobel, "technically pure", 96%
Water glass	Akzo-PQ Silica, "38-40Be, SiO <sub>2</sub> /Na <sub>2</sub> O = 3.27 - 3.33"

25

The BET surface area was analyzed in accordance with the method described by Brunauer, Emmet, and Teller, *The Journal of the American Chemical Society*, Vol. 60, page 309, 1938.

The CTAB surface area was analyzed in accordance with method NFT 45007, November 1987.

The DBP oil absorption was analyzed in accordance with method ASTM D 1208.

The water absorption expressed in wt.% is defined as the weight difference between the dry sample and the wetted sample. The water activity is equal to the water absorption per unit of BET Surface Area. The amount of absorbed water depends on the surface area of the silica. The water activity should therefore be compared to the water absorption of silica particles with different surface areas.

$$H_2O_{\text{activity}}(\mu\text{mol} \cdot \text{m}^{-2}) = \frac{1}{SA(\text{m}^2 \cdot \text{g}^{-1})} \cdot \frac{H_2O_{\text{absorption}}(\text{wt}\%)}{100} \cdot 10^6$$

$$18.02(\text{g} \cdot \text{mol}^{-1})$$

To increase reproducibility, a reference sample is always incorporated into the measurement cycle and the water activity of all samples is expressed relative to this reference sample. By definition, the water activity of this reference sample is 1.00.

Improvements to the unmodified silica are expressed as percentages, setting the unmodified silica at 100%.

#### Example 1

Silica particles were prepared according to methods A-D.

### Method A

(Comparison example not containing boron or aluminum)

The precipitated silica was suitably produced in the following way:

- 5 A well-stirred vessel of 0.030 m<sup>3</sup> was charged with about 16.4 kg of demineralized water containing about 20 ppm Ca<sup>2+</sup>. The contents were heated to 80°C and maintained at this temperature throughout the following steps.
- Water glass (SiO<sub>2</sub>/Na<sub>2</sub>O weight ratio about 3.3, containing 18.5 wt.% of SiO<sub>2</sub>, and having a density of about 1.225 g/ml) was dosed to the vessel at a rate of
- 10 75 g/min, for 90 min, so that about 6.6 kg of water glass were dosed. While the water glass was being dosed, sulfuric acid (18 wt.%) was dosed as well. The dosing rate was chosen such that the pH during the precipitation of the silica was 9.3. About 2.8 kg of sulfuric acid (17.5 wt.%) were dosed. When the dosing was stopped, the reaction mixture was allowed to after-react at said pH for 15
- 15 min. Next, sulfuric acid was dosed in 10 min, so that the pH was lowered to 7.5. About 0.5 kg of sulfuric acid (17.5 wt.%) was needed for this purpose. Water glass (18.5 wt.% of SiO<sub>2</sub>) was again dosed to the reactor at about the same rate as before for 45 min. About 2.8 kg of water glass were dosed. Sulfuric acid was dosed at the same time to ensure that the pH was kept constant at 7.5. About
- 20 1.4 kg (17.5 wt.%) were needed for this purpose. When the dosing was stopped, sulfuric acid was dosed in 20 min, so that the pH was lowered to 4.0. About 0.2 kg of sulfuric acid (17.5 wt.%) was needed for this purpose. The precipitated silica was removed from the reactor, washed in a conventional way, by means of a filter press, and dried using a spin flash dryer.

25

### Method B

- Silica was prepared in the same manner as in method A, but 36.2 g of boric acid were dissolved in the water glass solution. This boric acid/water glass solution was added simultaneously with sulfuric acid to a reactor containing
- 30 water ("the heel"). The resulting precipitated amorphous boron-containing silica (boron built in throughout the entire structure) was filtered, washed, and dried.

Method C

Silica was prepared in the same manner as in method A, but 36.2 g of boric acid were dissolved in the water glass solution. Instead of 0.2 kg of sulfuric acid, 0.3 kg of aluminum sulfate solution was added to lower the pH to 4.0.

5

Method D

Silica was prepared in the same manner as in method A, but instead of 0.2 kg of sulfuric acid, 0.3 kg of aluminum sulfate solution was added to lower the pH to 4.0.

10

In all methods A-D the following solutions were used:

The water glass solution contained approx. 18.5 wt.% SiO<sub>2</sub> and in methods B and C 0.067 wt.% boron was used. In methods C-D the Al<sub>2</sub>(SO<sub>4</sub>)<sub>3</sub> solution used had a concentration of approx. 17.5 wt.% and was only used for the acidification

15

from pH 7.5 to pH 4.0. The silica particles were spin flash dried.

Table 1.

Analyses of the boron-containing silica particles prepared according to methods A-D

↓

method	DBP ml/100g	w.a. %	SA BET m <sup>2</sup> /g	CTAB m <sup>2</sup> /g	B (wt.%)	Al <sup>#</sup> (wt.%)
A	211	100	187	171	0	0.11
B	221	106	184	163	0.06	0.11
C	222	110	184	161	0.06	0.27
D	202	108	186	162	0	0.27

20

<sup>#</sup> 0.11 wt.% Al was present as contamination in the silica

Table 1 makes clear that the incorporation of boron via method B (the water glass solution containing 0.067 wt.% boron) results in a significant increase in the water absorption and concomitantly in an increase in the DBP oil

25

absorption.

An increase in the water absorption has a positive influence on the coupling reaction between silica and a silane coupling agent, an increase in the DBP absorption has a positive influence on the dispersion in rubber blends.

When method C was used, the synergistic effect of aluminum was clearly shown.

When a water glass solution containing 0.134 wt.% boron was used, the water absorption increased further while the DBP remained on the same level as when water glass containing 0.067 wt.% boron was used, see Table 2.

Table 2.

Analyses of the boron-containing silica particles prepared according to methods B\* and C\*

method	DBP ml/100g	w.a. %	SA BET m <sup>2</sup> /g	CTAB m <sup>2</sup> /g	B (wt.%)	Al <sup>#</sup> (wt.%)
B*	224	110	184	163	0.12	0.11
C*	225	121	179	156	0.11	0.27

\* 0.11 wt.% Al was present as contamination in the silica

Note: Methods B\* and C\* are the same as methods B and C, respectively, but the water glass solution contains 0.134 wt.% boron.

When the boron concentration in water glass was increased to 0.201 wt.%, the water activity increased even further while the DBP remained on the same level as when the 0.067 or 0.134 wt.% boron in water glass solution was used.

The positive effects of built-in boron are not limited to the silica prepared according to the above-described method. In Table 3 the effects of boron incorporation and of boron and aluminum incorporation are given for a different grade of silica. Both the water activity and the DBP values increase. The

synergistic effect of built-in aluminum is given here for both the water activity and the DBP absorption.

The silicas I-IV were prepared by simultaneously adding sulfuric acid and water glass, optionally containing boron (II-IV), to a reactor at a temperature of 70°C and a pH of 9.3 for 150 min. After this, the reactor contents were acidified to pH 4 using sulfuric acid (silica I and silica II), or, alternatively, using an aluminum sulfate solution (silica III and silica IV).

Table 3.

silica	DBP ml/100g	w.a. %	SA BET m <sup>2</sup> /g	CTAB M <sup>2</sup> /g	B (wt.%)	Al <sup>#</sup> (wt.%)
I	206	100	205	161	0	0.1
II	225	116	199	152	0.06	0.1
III	257	124	207	152	0.05	1.1
IV	254	139	206	152	0.18	1.1

\* 0.1 wt.% Al was present as contamination in the silica

Silica I: not containing boron or aluminum

Silica II: modified with boron (0.06 wt.%)

Silica III: modified with boron (0.05 wt.%) and aluminum

Silica IV: modified with boron (0.18 wt.%) and aluminum

### Example 2

In this example the influence of the addition of B in comparison with the addition of P was determined.

Boric acid was added to the heel of the reaction mixture. The experiment proceeded as follows. First water was inserted into the reactor and subsequently boric acid was added to this amount of water (called "heel"). After complete dissolution, water glass and acid were added simultaneously to this water, maintaining a constant pH in the range between 7 and 10. After a reaction period, the reaction mixture was acidified to a pH of approximately 4, and the reaction mixture was filtered, washed, and dried (entry i).

In a similar experiment B was added in the form of boric acid during the simultaneous addition of water glass and acid (entry ii). In another experiment P was added in the form of phosphoric acid to the reaction mixture during simultaneous addition of the water glass and acid (entry iii). Alternatively, P was added in the form of phosphoric acid to the reaction mixture during the acidification step. The reaction was performed in exactly the same manner as described above, except that P was added by acidifying the reaction mixture from reaction pH (between 7 and 10) to pH 4 with phosphoric acid (entry iv). Standard silica was made in the same manner, but without addition B or P (entry 0).

	DBP ml/100g	w.a. %	SA BET m <sup>2</sup> /g	CTAB m <sup>2</sup> /g
entry 0	220	100	223	158
entry 1	236	109	198	162
entry 2	225	109	200	161
entry 3	224	92	224	163
entry 4	215	100	218	161

It can be concluded that with regard to the standard silica the addition of B leads to increased activity, decreased BET/CTAB ratio, and increased DBP, whereas these values remain unchanged when P rather than B was added.

Claims

1. An amorphous silica particle comprising 0.1 to  $10^5$  ppm boron atoms, characterized in that the boron atoms are covalently bonded to the oxygen atoms of the silica network.  
5
2. The amorphous silica particle of claim 1, comprising 10 to 125,000 ppm boron atoms.
- 10 3. The amorphous silica particle of claim 1 or 2, further comprising 0.05 to 15 wt.% aluminum atoms which are covalently bonded to the oxygen atoms of the silica network.
- 15 4. The amorphous silica particle of claim 3, comprising 0.8 to 2 wt.% aluminum atoms.
- 20 5. The amorphous silica particle of any one of claims 1-4 wherein the BET surface area is 30-500 m<sup>2</sup>/g, the CTAB surface area is 30-350 m<sup>2</sup>/g, the DBP oil absorption is 100-400 ml/100g, and the moisture content is >2 wt.%.
- 25 6. The amorphous silica particle of any one of claims 1-5 wherein the boron atoms, and optionally the aluminum atoms, are predominantly contained in the surface of the silica particle.
7. A process to make the amorphous silica particle of any one of claims 1-6 comprising the steps of reacting an aqueous solution of water glass with boric acid and/or borax, and optionally also with an aluminum salt.
- 30 8. Use of the amorphous silica particle of any one of claims 1-6 as a reinforcing filler for rubber articles, particularly for tires.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/02319

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C01B33/18 C01B33/193 C09C1/30 C08K3/36 C08K3/38

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, INSPEC, COMPENDEX, CHEM ABS Data, EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 631 982 A (GOODYEAR TIRE & RUBBER) 4 January 1995 (1995-01-04) claims 1,2,4,13,14,16,20,22 column 4, line 53 -column 7, line 24 column 11, line 47 -column 12, line 12 ---	1-8
A	EDAHIRO T ET AL: "Deposition properties of high-silica particles in the flame hydrolysis reaction for optical fiber fabrication" JAPANESE JOURNAL OF APPLIED PHYSICS, NOV. 1980, JAPAN, vol. 19, no. 11, pages 2047-2054, XP002145269 ISSN: 0021-4922 * page 2048, " 2. Experimental procedures" * page 2049, " 3.2 SiO2-B2O3 system" * --- -/--	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*Z\* document member of the same patent family

Date of the actual completion of the international search

29 June 2001

Date of mailing of the international search report

31/07/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040. Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Rigondaud, B

## INTERNATIONAL SEARCH REPORT

International Application No

PC1/EP 01/02319

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JUBB N J ET AL: "The processing of monodisperse boron-doped SiO <sub>2</sub> /sub 2/ particles" JOURNAL OF MATERIALS SCIENCE, JUNE 1987, UK, vol. 22, no. 6, pages 1963-1970, XP002145288 ISSN: 0022-2461 the whole document ----	1,2,5
A	DE 27 16 225 A (DEGUSSA) 26 October 1978 (1978-10-26) cited in the application the whole document ----	1,8
A	DATABASE CHEMABS Online! CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; ZHUKOVA, L. A. ET AL: "Study of silicon dioxide doped with boron oxide by an IR-spectroscopic method" retrieved from STN Database accession no. 88:200428 CA XP002145289 abstract & IZV. AKAD. NAUK SSSR, NEORG. MATER. (1978), 14(4), 687-90, 1978, ----	1
A	EP 0 044 236 A (RHONE POULENC CHIM BASE) 20 January 1982 (1982-01-20) page 2, line 31 -page 4, line 9 ----	7
A	DATABASE WPI Section Ch. Week 199049 Derwent Publications Ltd., London, GB; Class A60, AN 1990-367416 XP002145309 & SU 1 541 189 A (AS UKR SURFACE CHEM), 7 February 1990 (1990-02-07) abstract ----	
A	DATABASE WPI Section Ch. Week 197713 Derwent Publications Ltd., London, GB; Class A60, AN 1977-22433Y XP002145310 & JP 52 019197 A (SHINETSU CHEM IND CO LTD), 14 February 1977 (1977-02-14) abstract -----	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC1/EP 01/02319

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0631982	A	04-01-1995	CA 2105719 A US 6068694 A	29-12-1994 30-05-2000
DE 2716225	A	26-10-1978	NONE	
EP 0044236	A	20-01-1982	FR 2486514 A FR 2499540 A AT 7778 T AU 548330 B AU 7281081 A BR 8104429 A CS 234030 B DE 3163969 D IE 52048 B JP 1043696 B JP 1569528 C JP 57047712 A KR 8402018 B PT 73349 A, B US 4503158 A	15-01-1982 13-08-1982 15-06-1984 05-12-1985 14-01-1982 30-03-1982 14-03-1985 12-07-1984 27-05-1987 22-09-1989 10-07-1990 18-03-1982 05-11-1984 01-08-1981 05-03-1985
SU 1541189	A	07-02-1990	NONE	
JP 52019197	A	14-02-1977	JP 1024273 C JP 55014810 B	28-11-1980 18-04-1980